

Le Rouge

Benefits

Comparison with and without EstoGel®:
Lipstick with EstoGel® glides on the skin. It is easy to apply, leaving an even, full-coverage film with a glossy finish.



PHASE	TRADE NAME	RAW MATERIAL	SUPPLIER	%
A	EstoGel® M	Castor Oil/IPDI Copolymer (and) Caprylic/Capric Triglyceride	PolymerExpert	5,00
A	Castor Oil	Ricinus Communis (Castor) Seed Oil	-	29,30
A	DUB MCT 5545	Caprylic/Capric Triglyceride	Stéarinerie Dubois	26,50
B	Cetiol Ultimate	Undecane (and) Tridecane	BASF	10,00
C	Rice Bran Wax	Oryza Sativa (Rice) Bran Wax	-	9,00
C	Candelilla Wax	Euphorbia Cerifera (Candelilla) Wax	-	7,50
C	Nat Hazelnut T. Butter	Corylus Avellana (Hazelnut) Seed Oil (and) Hydrogenated Hazelnut Oil	Naturochim	3,00
D	COD-8001 D&C Red 7 Ca Lake	Ricinus Communis (Castor) Seed Oil (and) Red 7 Lake	Maprecos	6,10
D	COD-8009 FD&C Yellow 5 Al Lake	Ricinus Communis (Castor) Seed Oil (and) Yellow 5 Lake	Maprecos	1,10
D	Sunshine® Blush Bronze	Synthetic Fluorophlogopite (and) Titanium Dioxide (and) Iron Oxides	Maprecos	2,00
E	Vanille Gourmande	Fragrance	Mane	0,50

Process

- Heat up A to 100°C under stirring
- At 100°C, disperse the polymer for 30 minutes
- Cool down to 85°C
- Add B and stir until the blend is homogeneous
- Add C and stir until the blend is homogeneous
- Add D and homogenize
- Introduce the fragrance and blend
- Pour into a mold