

Natural Suncare

Benefits

- Natural sun care formulated with mineral filters
- EstoGel® Green ensures optimum emulsion stability and improves application to the skin
- Non-sticky, almost transparent finish on the skin



PHASE	RAW MATERIAL	%
A	Demineralized Water	41,50
A	Sodium Chloride	1,00
A	Glycerin	3,00
B	EstoGel® Green	2,00
B	Titanium Dioxide (and) Caprylic/Capric Triglyceride (and) Stearic Acid (and) Alumina (and) Polyhydroxystearic Acid	14,00
B	Zinc Oxide	14,00
B	Coco-Caprylate Caprate	20,00
C	Polyglyceryl-3 Diisostearate	2,00
C	Polyglyceryl-2 Dipolyhydroxystearate	2,00
D	Fragrance	0,50

Process

- In a secondary beaker, introduce A and solubilize NaCl
- In the main beaker, introduce B and heat up to 80°C under stirring
- At 80°C, stir for 30min
- Cool down to 40°C
- Add C to B and stir for 5 min
- Make the emulsion pouring A into B+C for 15 min
- Add D and homogenize