

Sun Protection Gel

Benefits

- Thick, perfectly transparent gel
- Sprayable formula



PHASE	RAW MATERIAL	%
A	Butyl Methoxydibenzoylmethane	3,00
A	Octocrylene	8,00
A	Ethylhexyl Salicylate	5,00
A	Homosalate	10,00
A	Synoxyl® HSS	1,00
A	C12-15 Alkyl Benzoate	68,80
A	EstoGel® M	4,00
B	Fragrance	0,20

Process

- Add the ingredients of the phase A in a beaker
- Heat to 100°C with gentle stirring
- At 100°C, unfold the polymer under moderate stirring for 30 minutes
- Cool to 40°C
- Add the fragrance and homogenize
- Cool to 30 - 35°C and pour into a suitable packaging