

# AquaStick

*The freshness of water, the comfort of cream*

## Benefits

- Incorporate large volumes of water into your sticks
- An ultra-fresh solid stick that applies like a cream

PHASE	TRADE NAME	INCI NAME	SUPPLIER	%
A	Demineralized Water	Water	-	45.30
A	Phenoxyethanol	Phenoxyethanol	-	0.60
A	Glycerin	Glycerin	-	3.00
A	Physiogenyl®	Sodium PCA (and) Magnesium PCA (and) Zinc PCA (and) Manganese PCA	Solabia	1.00
A	Blue 1 (sol. 0.5%)	-	-	0.10
<b>B</b>	<b>EstoGel® Max</b>	<b>Castor Oil/IPDI Copolymer (and) Caprylic/Capric Triglyceride (and) Hydrogenated Castor Oil/Sebacic Acid Copolymer</b>	<b>PolymerExpert</b>	<b>5.00</b>
B	Eutanol G	Octyldodecanol	BASF	6.00
B	Cetiol C5 C	Coco-Caprylate Caprate	BASF	16.30
B	Rice Bran Wax	Oryza Sativa (Rice) Bran Wax	-	5.00
B	Candelilla Wax	Euphorbia Cerifera (Candelilla) Wax	-	5.00
B	Beeswax	Beeswax	-	3.00
B	Lanette 16	Cetyl Alcohol	BASF	3.00
B	Hydriol PGMO.4	Polyglyceryl-4 Oleate	DKSH Spain	1.00
C	Fragrance Aqua Zen	Fragrance	-	0.50
C	Tocopherol	Tocopherol	-	0.20
D	Corn Starch	Zea Mays (Corn) Starch	Sensient	5.00

## Process

- Heat up B to 85°C and homogenize for 30 minutes
- Cool down B to 80°C
- Heat up A to 80°C
- Add A to B under high shear for 15 minutes
- Add C and homogenize
- Add D and homogenize
- Pour into a suitable packaging